



UP-40 Long-wearing UHMW Polyethylene

Material Data Sheet
M-5 (Rev. 01; 08-08-17)

19650 Pauling
Foothill Ranch, CA
USA 92610-2610
t +1 949 460 2100
f +1 949 460 2300

Jollemanhof 16, 5th floor
1019 GW Amsterdam
The Netherlands
t +31 20 638 6523
f +31 20 625 6018

Suite 901, Chinachem
Century Tower
178 Gloucester Road,
Wanchai, Hong Kong
t +852 28681860
f +852 22956753

www.balseal.com



Overview

UP-40 is an ultra-high molecular weight (UHMW) polyethylene-based material similar to UP-30, but made from a lower molecular weight polyethylene. It was designed for high-performance liquid chromatography (HPLC) pumps, and offers excellent sealing performance in reciprocating applications from cryogenic, -450 °F to 180 °F (-268 °C to 82 °C).

Chemical Compatibility

UP-40 is compatible with acids and bases. This material is compatible with most fluids. For more compatibility information, request report TR-60A, or go to www.balseal.com/technical-library. Select Technical Reports, then select TR-60A Chemical Compatibility Guide.

FDA and USP Compliant

UP-40 is FDA compatible for use in food contact. Bal Seal Engineering defines “FDA compatible” as compositions where the majority (97% or more) of the ingredients have received an FDA “safe for use in food contact” review.

Color

Yellow-gold

Mechanical Properties of UP-40

ASTM Standard	Tensile Strength at Break Typical	Elongation at Break Typical
D638	6400 psi (441 bar)	320%

Advantages of UP-40

- Suitable for medium pressure reciprocating and rotary applications
- High chemical resistance
- High wear and pressure/extrusion resistance
- Temperature range of -450 °F to 180 °F

Other Information

For additional information, please contact a technical sales representative at one of our offices nearest you. Bal Seal Engineering, Inc. maintains a vast library of material references and testing information.

The information, descriptions, recommendations and opinions set forth herein are offered solely for your consideration, inquiry, and verification and are not, in part or in whole, to be construed as constituting a warranty, expressed or implied, nor shall they form or be a part of the basis of any bargain with Bal Seal Engineering, Inc.. If any sample or model was shown to or provided by Buyer/User, such sample or model was used merely to illustrate the general description and type of goods. Such use is not to be construed as a warranty that the goods will conform to the sample or model. Furthermore, THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND ALL OTHER WARRANTIES, IMPLIED OR EXPRESSED, ARE EXCLUDED AND SHALL NOT APPLY. This document provides product options for further investigation by Buyers/Users having technical expertise. The Buyer/User, through its own analysis and testing, is solely responsible for making the final selection of the products and for assuming that all performance, safety and warning requirements for the application are met. It is recommended that Buyers/Users run evaluation testing under actual service conditions to determine whether proposed Bal Seal Engineering products are suitable for the intended purpose. Nothing contained herein or in any of our literature shall be considered a license or recommendation for any use that may infringe patent rights. (LE-17)

©Copyright 2017 Bal Seal Engineering, Inc. U.S.A.