

High-Performance Polymer (P-41 HT)

P-41 HT is suitable for sealing viscous and abrasive materials in scraping-action applications at elevated temperatures. **P-41 HT** performs well in low surface-speed applications, and has superior tensile strength and excellent chemical compatibility.

P-41 HT has high temperature and extrusion resistance, but has limited flexibility at temperatures below 200 °F (93°C). **P-41 HT** is recommended for scraping applications that require higher extrusion resistance and longer life. Operating temperatures range from -70 °F to +550 °F (-57 °C to +288 °C).

Chemical Compatibility

P-41 HT has excellent chemical compatibility, but is not recommended for use with strong acids, such as nitric, sulfuric and hydrofluoric acids. For more details, reference Technical Report TR-60A in our online technical library at www.balseal.com.

FDA Compliance

P-41 HT is made from an “FDA compliant” resin for use in food contact applications.

Radiation Resistance

Suitable to 10⁹ rads.

Mechanical Properties

The mechanical properties of **P-41 HT** at ambient temperatures are:

Tensile strength	ASTM D638	14,000 psi Min. (982 kg/cm ²)
Elongation	ASTM D638	25% Min

Color

Beige

Advantages of P-41 HT

- Superior tensile strength
- Excellent extrusion resistance
- Excellent chemical compatibility
- Excellent temperature stability to 500°F (260°C)

Other Information

For additional information, please contact a Technical Sales Representative at (949) 460-2100. We maintain a vast library of material references and testing information.

It is essential that the customer run evaluation testing under actual service conditions with a sufficient safety factor to determine if the proposed, supplied, or purchased, Bal Seal Engineering products are suitable for the intended purpose and to confirm expected results. Bal Seal Engineering makes no warranty, express or implied, regarding Bal Seal Engineering products or of the information contained herein, including but not limited to, warranties of merchantability, performance, and fitness for a particular use or purpose. Bal Seal Engineering shall not be liable for any loss or damage of any kind or nature that may result from the use of, reference to, or reliance on, the information contained herein, including, but not limited to, consequential, special (including loss of profits) direct, indirect, incidental, or similar damages, even if Bal Seal Engineering has been advised of the possibility of such damages. © 2010 RT-56 (50-434) M-33 Rev B (632-32 and 623-64) 04-13-10

U.S. Address 19650 Pauling Foothill Ranch, CA 92610-2610 • Telephone: (949) 460-2100 • Fax: (949) 460-2300
BV Address: Jollemanhof 16, • 1019 GW Amsterdam • The Netherlands • Telephone: 31 20 638 65 23 • Fax: 31 20 625 60 18
Bal Seal Engineering, Inc. is certified to [ISO 9001](http://www.iso9001.com) | www.balseal.com